



PRODUCTS AT A GLANCE

KEY TO KRETUS® MIX & MATCH PRODUCTS

AP = All Purpose	MVR = Moisture Vapor Reducer
EZ = Slow Cure/Low Application Temps & Humidity	TH = Traditional
FC or FAST = Fast Cure, High Application Temps & Humidity	UV = UV Resistant

Top Shelf® Epoxy: 100% Solids Epoxy for Floors, Walls, Countertops & More! Clear or Color Finish.
Combine any part A with any part B.

PART A	Mix Ratio (volume)	PART B	Substrate MVER RH	Application Temperature	Working Time	Recoat Time	Return to Service	Full Cure
All Purpose A-RESIN	2A:1B	MVR-EZ	25 lbs. 99%	60-95°F <90% RH	25-30 m	8.5-24 h	24 h	7 days
Countertop CAST-RESIN	2A:1B	MVR-FC	25 lbs. 99%	41-77°F <90% RH	15 m	3-16 h	5-6 h	5 days
Wall Cove COVE-RESIN	2A:1B	EZ	10 lbs. 80%	60-110°F <90% RH	40-50 m	9-36 h	24 h	7 days
Chemical Resistance CR-RESIN	2A:1B	AP	10 lbs. 80%	60-95°F <90% RH	25-35 m	7.5-36 h	24 h	7 days
Low Gloss LG-RESIN	2A:1B	TH	3 lbs. 80%	60-80°F <90% RH	20-25 m	8-24 h	24 h	7 days
Terrazzo T-RESIN	5A:1B	FAST	10 lbs. 80%	41-85°F <90% RH	15-20 m	5.5-24 h	10 h	5 days

WB Epoxy: Water-based Epoxy for Floors and Walls! Clear or Color Gloss Finish.
Combine any part A with part B.

PART A	Mix Ratio (volume)	PART B	Substrate MVER RH	Application Temperature	Working Time	Recoat Time	Return to Service	Full Cure
A	4A:1B	B	5 lbs. <80%	40-100°F <90% RH	30 m	2-24 h	16 h	7 days
CONDUCTIVE PRIMER A	4A:1B							

Acrylic Polymer Concrete & Acrylic Primer: Great for Waterproof Decking! Gray or White Finish.
Combine Acrylic Admix with any part B. Bonder Resin can be used alone or with any part B.

PART A	Mix Ratio (weight)	PART B	Substrate MVER RH	Application Temperature	Working Time	Recoat Time	Return to Service	Full Cure
ACRYLIC ADMIX	Based on application method	BASE COAT 16 mesh	10 lbs. 90%	45-100°F 5-85% RH	25-30 m	2-24 h	24 h	28 days
		TEXTURE 2.0 20 mesh	10 lbs. 90%	45-100°F 5-85% RH	20-25 m	2-24 h	24 h	28 days
		TEXTURE 3.0 30 mesh	10 lbs. 90%	40-100°F 5-85% RH	20-25 m	2-24 h	24 h	28 days
PRIMER: BONDER RESIN			3 lbs. 90%	45-100°F <80% RH	20-25 m	2-6 h	N/A	24 h

UPC (Urethane Polymer Concrete): 100% Solids and No Prime Coat Required! Matte Color Finish.
Combine UPC products only if they have the same 2-letter code: **RC** with **RC**, **SL** with **SL**, and so on.

PART A	PART B	Application Temperature	Working Time	Recoat Time	Return to Service	Full Cure	PART C	Mix Ratio (weight)	Substrate MVER RH
RC/TT	EZ	60-90°F <80% RH	30 m	12 h	24-36 h	7 days	Roll Coat, 5-30 mils	6A:6B:6C	15 lbs. <99%
SL/MF							Self-leveler, 1/8-1/4"		25 lbs. <99%
WC/VC	AP	40-80°F <70% RH	20 m	8 h	12-16 h	5 days	Medium-fill SL, 1/8-1/4"	8A:8B:25C	25 lbs. <99%
							Trowel-applied, 1/4-1"		25 lbs. <99%
	FC	40-80°F <45% RH	10 m	3 h	2-5 h	3 days	Wall Cove, 1-10"	3A:3B:30C	N/A
							Vertical Coat, 3-8 mils		N/A
							VC	3A:3B:3.50C	N/A

Application temperatures are recommended. To install systems at higher or lower temps, contact manufacturer.

All times recorded using 1-qt. sample at ambient temperature of 70°F and 50% RH. Top Shelf® Epoxy recorded using A-Resin.



PRODUCTS AT A GLANCE

UV-RESISTANT!

UPC UV: 100% Solids and No Prime Coat Required! Matte Color Finish.
Combine parts A, B, and C with 6 oz Poly Accelerant.

PART A	PART B	Application Temperature	Working Time	Recoat Time	Return to Service	Full Cure	PART C	Mix Ratio (weight)	Substrate MVER RH
RC/TT	RC UV AP	40-100°F <90% RH	30 m	12 h	24-36 h	7 days	Roll Coat, 5-30 mils RC	6A:6B:6C	15 lbs. <99%

Polyaspartic: Highest UV Resistance! Clear or Color Finish.

Combine products with the same 2-number code: **72** with **72**, **85** with **85**, and so on.

PART A	Application Temperature	Working Time	Recoat Time	Return to Service	Full Cure	PART B	Mix Ratio (volume)	Substrate MVER RH
92 Low Odor EZ	<80°F <55% RH	15-25 m	6-24 h	24 h	5 days	92 LOW ODOR B 100% solids	1A:1B	3 lbs < 80%
92 Low Odor FAST	<80°F <35% RH	15-20 m	3-24 h	24 h	3 days			
92 Low Odor XFC	<70°F <35% RH	5-10 m	1-6 h	12 h	3 days			
85 EZ	<90°F <80% RH	15-25 m	8-36 h	36 h	7 days	85 85% solids	1A:1B	3 lbs < 80%
85 FAST	<80°F <35% RH	15-20 m	4-24 h	24 h	5 days			
85 XFC	<70°F <35% RH	5-10 m	1-6 h	12 h	3 days			
72 EZ	<100°F <80% RH	25-30 m	8-36 h	36 h	7 days	72 72% solids	1A:1B	3 lbs < 80%
72 FAST	<90°F <70% RH	20-25 m	4-24 h	24 h	5 days			

Polyurethane: HP = Highest Chemical Resistance! **HS** = Highest Shine! Clear or Color Finish.

Combine products with the same 2-letter code: **HP** with **HP** or **HS** with **HS**.

PART A	Application Temperature	Working Time	Recoat Time	Return to Service	Full Cure	Mix Ratio (volume)	PART B	Substrate MVER RH
HP Gloss	60-90°F <70% RH	20 m	4-6 h	12 h	5 days	1A:4B	HP B 3-5-mil high performance	3 lbs < 80%
HP Satin	60-80°F <55% RH	15-20 m	4-6 h	12 h	7 days	1A:2B		
HS EZ	60-110°F <90% RH	30-45 m	6-8 h	48 h	7 days	2A:1B	HS B 8-16-mil high shine	3 lbs < 80%
HS FC	40-80°F <40% RH	15-20 m	2-4 h	12 h	7 days	2A:1B		

Acrylic Sealer: Clear and Color Finishes for Concrete, Masonry, and Wood.

WB BASES must be combined with **WB Colorant**. **SB** = solvent-based **WB** = water-based

SEALER	Appearance	Application Temperature	Working Time	Recoat Time	Return to Service	Full Cure	Substrate MVER RH
SB GLOSS or LOW GLOSS	Clear Translucent (if pigmented)	35-85°F <80% RH	10 m	1-24 h	18-48 h	7 days	3 lbs < 80%
WB GLOSS or LOW GLOSS	Clear Translucent (if pigmented)	35-100°F <80% RH	20-25 m	2-48 h	24-48 h	7 days	3 lbs < 80%
WB BASE ACCENT	Opaque - white or pastel hues		20-25 m	2-48 h	24-48 h	7 days	3 lbs < 80%
WB BASE MEDIUM	Opaque - bright, rich hues						
WB BASE DEEP	Opaque - dark hues, jewel tones						