

Color Chart

COLOR QUARTZ

Broadcast KRETUS® Color Quartz into KRETUS Top Shelf® Epoxy, KRETUS® Polyaspartic, Polyurethanes, and Urethane Polymer Concrete to transform ordinary floors and walls into inviting living and working spaces.



General Mixing Guide

Ensuring uniform color: Check that product batch numbers are the same. Different batch numbers can produce slight variance in color. If different batch numbers, box product together and blend thoroughly before mixing product with other components. Always test application on site.

Broadcasting: To keep quartz from disappearing into coating, allow coating to cure for 10–15 minutes. Then broadcast quartz according to desired look. If fast hardeners used, broadcast after 5 minutes.

Broadcast Coverage Rate	
Product	#20/#30 Grade
Polyaspartic 72, 85, 92LO	0.5–0.75 sf./lb.
Top Shelf® Epoxy	0.5–0.75 sf./lb.
Urethane Polymer Concrete MF, SL, or TT	1 sf./lb.
Urethane Polymer Concrete RC	0.5–0.75 sf./lb.

Colors are shown as examples only. KRETUS® does not manufacture or distribute color quartz and color chip. Color and availability depend on the customer's chosen manufacturer and distributor.

DISCLAIMER: The information contained in this document is intended for use by KRETUS GROUP® qualified and trained professionals. This is not a legally binding document and does not release the specifier from his/her responsibility to apply materials correctly under the specific conditions of the construction site and the intended results of the construction process. The most current valid standards for testing and installation, acknowledged rules of technology, as well as KRETUS GROUP® technical guidelines must be adhered to at all times. The steps given in this document and other mentioned documents are critical to the success of your project.