



## KVP PRIMER / SEALER | 140

---

### Interior Water-Based Pigmented PVA Sealer

KRETUS® KVP PRIMER / SEALER | 140 is a water-based, pigmented PVA sealer formulated for interior use on drywall and plaster. It effectively seals the substrate, creating a smooth, uniform surface with excellent enamel holdout for a variety of top coats.

#### ADVANTAGES

- SCAQMD—complies with Rule 1113, Architectural Coatings
- Proprietary substitute for TT-P-650
- Non-EG Certified—formulated without Ethylene Glycol (Non-EG)
- Manufactured using 100% solar energy

#### SUGGESTED USES AND APPLICATION AREAS

- new interior drywall and plaster

#### FINISH

- Flat

#### LIMITATIONS

- NOT recommended for use over previously painted surfaces.

#### PACKAGING

- 5-gallon container

Larger sizes may be available through KRETUS® distributor.

#### SAFETY, STORAGE, TESTING, AND WARRANTY

- **Safety:** Personal protective equipment and safety conditions must be considered before using any product. Review all relevant and current documentation including Safety Data Sheets ([kretus.com/safety-data-sheets](https://kretus.com/safety-data-sheets)).
- **Storage area:** Store material in a dry area, outside of direct sunlight between 60°F and 80°F.
- **Testing:** Before installation: Test and look for any unknown site conditions and/or defects. To ensure desired results are achieved, the system should be tested in a small area on site before full installation begins.
- **Warranty:** For warranty to be upheld, Pre- and Post-Job Checklists ([kretus.com/project-planning](https://kretus.com/project-planning)) must be completed.

#### SURFACE PREPARATION

- Surfaces must be clean, dry and free from all contaminants that may impair adhesion.
- Glossy or slick surfaces must be scuff sanded prior to application.

#### APPLICATION

Brush, roll or spray. Ambient and surface temperatures must be above 55°F and relative humidity below 80%. Clean tools and equipment with soap and water.

**DRYING TIME**

Touch	30 min
Recoat	2 hr

**COVERAGE**

- 250 to 400 square feet per gallon, depending on porosity and texture of the surface

Coverage rates are for estimating purposes only. Factors such as waste, unusual/abnormal substrate conditions, and other unforeseen jobsite conditions may affect actual product yields and are the responsibility of the installer.

**MIL THICKNESS**

Wet	3.7
Dry	1.2

**THINNING**

Use at package consistency. If thinning is required, use water sparingly

**COMPOSITION**

Titanium Dioxide .....	7.2%
Extenders .....	18.5%
TOTAL PIGMENT .....	25.7%
Resin .....	17.3%
Additives .....	8.9%
Water .....	48.7%
TOTAL VEHICLE .....	74.9%

Weights and Measurements +/-3.0%	
Solids by Volume.....	32.4%
Solids by Weight .....	43.9%
VOC.....	94 g/L
Weight per Gallon.....	10.3 lbs
Viscosity .....	94-98 KU

**Disclaimer:** This document is intended for Kretus-trained professionals. It is not legally binding and does not remove the user's or specifier's responsibility to ensure materials are used appropriately for the project and jobsite. Always follow the most current industry standards and Kretus technical guidelines. **Note:** Subject to change without notice. For the latest version, visit [kretus.com](http://kretus.com).