



ACRYLIC SEALER WB BASE | ACCENT/MEDIUM/DEEP

Make Waterproofing Easy with Water-Based Acrylic Color

KRETUS® ACRYLIC SEALER WB BASE is a flexible, UV-resistant, water-based coating designed for easy color customization. Mix one WB Colorant with any of the three base coats—**ACCENT**, **MEDIUM**, or **DEEP**—to create light, medium, or dark shades. This coating also stays wet longer than solvent-based sealers, helping reduce brush and roller marks during application.

ADVANTAGES

- meets USDA, FDA, EPA, and SCAQMD standards
- eligible for LEED points
- antibacterial
- low maintenance
- low odor
- thermal shock resistance
- UV resistance
- waterproofing

SUGGESTED USES AND APPLICATION AREAS

- adhesion to concrete, wood, metal, non-glazed tiles
- prime, base, and top coats
- vertical surfaces
- interior/exterior
- industrial, commercial, residential, and occupied spaces

KRETUS® SYSTEMS

- Color Splash
- Waterproof and Concrete Overlays
- Waterproof Decking

For all KRETUS® systems, see kretus.com/systems.

FINISH AND COLOR

- gloss
- opaque color

Options

- **ACCENT BASE** for light color
- **MEDIUM BASE** for medium color
- **DEEP BASE** for dark color

See kretus.com/color-charts.

PRECAUTIONS AND LIMITATIONS

- **Application temperatures:** When temperatures increase or humidity decreases, material cures faster. Material cures slower when temperatures decrease or humidity increases. If application temperatures are outside of those recommended, contact your KRETUS® Technical Representative. Apply material when temperature is decreasing—adhere to the KRETUS® Dew Point Calculation Chart available at kretus.com/project-planning.

- **Prime coat:** A prime coat may be required when stem walls are highly absorbent, if outgassing is suspected or prevalent, or if concrete is very porous or in poor condition. All concrete repairs must be completed before installing any system.
- **Color:** Acrylic Sealer WB Base must be combined with **WB COLORANT**.
- **Film thickness:** DO NOT apply single coat greater than 16 mils thick (100 SF per gallon). DO NOT let material puddle on floor. This may cause white spots to appear when coating cures.
- **Mock-ups:** Complete samples and onsite mockups to ensure desired results are achieved.
- **Weather conditions:** DO NOT apply under direct sunlight. DO NOT install under inclement weather conditions.

COMPONENTS

Single Kit

- ACRYLIC SEALER WB BASE | ACCENT/MEDIUM/DEEP, 5 gal
- WB COLORANT, 16 oz

Larger sizes may be available through KRETUS® distributor.

SAFETY, TESTING, AND WARRANTY

- **Safety:** Personal protective equipment and safety conditions must be considered before using any product. Review all relevant and current documentation including Safety Data Sheets (kretus.com/safety-data-sheets).
- **Testing:** Before installation: Test and look for any unknown site conditions and/or defects. To ensure desired results are achieved, the system should be tested in a small area on site before full installation begins.
- **Warranty:** For warranty to be upheld, Pre- and Post-Job Checklists (kretus.com/project-planning) must be completed.

STORAGE AND APPLICATION TEMPERATURES

Ideal Storage Environment	Dry, Out of Direct Sunlight, 60-80°F
Material Temperature During Application	50-70°F and 5°F Above Dew Point
Minimum Substrate Temperature During Application	5°F Above Dew Point
Recommended Application Temperature	35-100°F, <80% RH (Relative Humidity)

Average Application Time

Ambient Temperature	35-100°F, <80% RH	50°F, 50 % RH	70°F, 50 % RH	100°F, 50 % RH
Working Time	20-25 min	30-35 min	20-25 min	10-15 min
Recoat Window	2-48 hr	2-48 hr	2-48 hr	2-24 hr
Return to Service (Foot Traffic)	24-48 hr	24-48 hr	24-48 hr	24 hr
Full Cure (Vehicle Traffic)	7 days	7 days	7 days	7 days

SURFACE PREPARATION

Before installing any coating, the substrate must be sound, meaning all necessary repairs have been completed. It must be properly prepared, clean, dry, and free of any contaminants, moisture, materials, or particles that may hinder material's adhesion to the substrate.

MIXING AND APPLICATION

Single Kit Mix Ratio	Acrylic Sealer: WB Colorant = 5 gal:16 oz
Spray Application	May be diluted with water at a ratio of up to 2 parts Acrylic Sealer to 1 part water (by volume).
Mixing Tool(s)	low-RPM, low-torque drill and Jiffler-style mixer

General Mixing Directions	Mix Base with WB Colorant for 1 minute or until uniform.
Adding Water	Add additive and mix for 1 minute(s) or until uniform.

Premeasure components to make sure you are using the correct mix ratio. Combine components according to mix instructions. Continue mixing until the coating's consistency is uniform. The coating must remain thoroughly mixed during the application.

Keep a wet edge while applying product. Wear spiked shoes when walking on material.

Coverage rates: Refer to the Acrylic Sealer General Overview (kretus.com/product-general-overviews) and the applicable Installation Guide (kretus.com/installation-guides) for project-specific coverage rates.

PROPERTIES WHEN FULLY CURED

PROPERTIES	TEST METHOD	TYPICAL VALUES
Abrasion Resistance	ASTM D4060	40 mg loss
Abrasion Resistance (with Anti-Slip)	ASTM D4060	24-30 mg loss
Adhesion To Concrete	ASTM D4541	300 psi
Flame Spread/Critical Flux	ASTM E648	Class 1
Flame Spread/Rate of Burning	ASTM D635	Self-extinguishing
Hardness (König)	ASTM D4366	130-140
Impact Resistance	ASTM D2794	140 in-lbs.
Moisture Vapor Emission Rate	ASTM F1869	<3 lbs.
Relative Humidity	ASTM F2170	<80%
Tensile Elongation at Break	ASTM D2370	10%
Tensile Strength	ASTM D2370	6,000 psi
UV Resistance	ASTM D4587	Level 2
Water Absorption	ASTM D570	0.1%
Yellowing Resistance	ASTM G154	< 3.0 ΔE, gray (color tested for visible changes)

CHEMICAL AND STAIN RESISTANCE

1 = Best for chemical resistance: Chemical has no adverse effects on fully cured coating; remove within 24 hours.

2 = Low potential for stain: Chemical has no adverse effects on fully cured coating if removed within 24 hours.

3 = High potential for stain or degradation: Chemical must be removed within 24 hours of exposure.

NR = Not recommended

Acetic Acid (Component of Vinegar), 10%	1	Formaldehyde, 37%	NR
Acetic Acid, 30%.....	NR	Premium Gasoline.....	1
Acetone.....	NR	Hydraulic Fluids (Machinery, Automobile, Aviation)	2
Ammonia, 30%.....	NR	Hydrochloric Acid, 10%.....	3
Ammonium Hydroxide, 30%.....	NR	Hydrochloric Acid, 30%.....	3
Antifreeze (Coolant).....	2	Hydrofluoric Acid, 10%	NR
Benzene (Component of Crude Oil).....	3	Hydrofluoric Acid, 30%	NR
Benzyl Alcohol	NR	Hydrogen Peroxide, 10%	NR
Betadine, 11%	NR	Hydrogen Peroxide, 50%	NR
Boric Acid, 4%.....	NR	Iodine, 2%.....	3
Brake Fluid, DOT 3	1	Isopropyl Alcohol	NR
Chromic Acid, 10%.....	3	Jet Fuel.....	1
Chromic Acid, 30%.....	NR	Lactic Acid, 30% (Dairy Facility).....	NR
Citric Acid, 30%.....	1	Lime Juice	2
Ethanol, 95%.....	NR	Magnesium Hydroxide.....	1
Ethyl Acetate, 99% (Food/Beverage Facility)	NR	MEK (Methyl Ethyl Ketone)	NR

Methanol	NR	Sodium Hydroxide (Caustic Soda), 50%	1
Methylene Chloride	NR	Sodium Hypochlorite (Bleach), 10%	NR
MIBK (Methyl Isobutyl Ketone).....	NR	Sodium Hypochlorite (Bleach), 30%.....	NR
Mineral Oil	1	Sodium Persulfate (Bleaching and Oxidizing Agent)	3
Motor Oil, SAE 30	1	Sulfuric Acid, 37% (Battery Acid)	NR
Mineral Spirits.....	NR	Tannic Acid, 20%.....	3
Mustard, Yellow	3	Tartaric Acid, 10%	3
Nitric Acid, 30%	NR	Transmission Fluid	2
Oleic Acid	1	Urine, Dog or Cat	2
Oxalic Acid, 10%.....	1	Urea (Nitrogen-Rich Fertilizer).....	1
Phosphoric Acid, 20%	NR	Vinegar, Distilled	1
Potassium Hydroxide, 30% (Alkaline Batteries, Soap Manufacturing).....	3	Water (Hard Water from Well)	1
Propylene Glycol.....	1	Whisky	2
Silver Nitrate, 20% (Photo Labs)	NR	Wine, Cabernet Sauvignon	2
Sodium Chloride, 20%.....	1	Xylene	NR

Pigments or colorants may affect working times, reduce chemical resistance, or increase potential for stain. Coatings tested at ambient temperature over 1-3 days' exposure to chemical. To ensure desired results are achieved, products should be tested on site before installation.

Disclaimer: This document is intended for Kretus-trained professionals. It is not legally binding and does not remove the user's or specifier's responsibility to ensure materials are used appropriately for the project and jobsite. Always follow the most current industry standards and Kretus technical guidelines. **Note:** Subject to change without notice. For the latest version, visit kretus.com.